

BLUSKY™ FLOWCRETE EPF

Solvent Free Thixotropic Epoxy Based Concrete Resurfacing Compound

Description

BLUSKY™ FLOWCRETE EPF is a solvent-free, moisture tolerant, thixotropic, two part skimmed coat/ putty, based on epoxy resins and special fillers, designed for use at temperatures between +5°C & +40°C. It is a soft pasty consistency material which gives a smooth finish mainly for fine concrete blow hole repair and resurfacing concrete structures before application of Epoxy or PU top coat. **BLUSKY™ FLOWCRETE EPF** is used in dam, bridges, industrial floors, walls and ceiling, windmills, etc.

Part- A : Base (White) Paste

Part- B : Hardener (Black) Paste

Mixed Material : Grey

Indicative Characteristics

| | |
|----------------------------------|-------------------------------|
| Mixing Ratio (Pack A: B), by wt. | 2:1 |
| Pot life, minutes, 30°C | More than 30 minutes |
| Touch dry | 3-6 hours |
| Hard dry | Over night |
| Full cure | 7 days |
| 1 day Compressive Strength | >40 MPa |
| 7 days Compressive Strength, | >60 MPa |
| 7 days pull off bond strength | >2 MPa (or concrete failure) |
| Mixed Density | 1.5 ±0.2 |

Domains of Application

Thixotropic - can be applied in uniform thickness on vertical and horizontal surfaces to rectify concrete blow holes and undulations. It can also use as adhesive to join steel, aluminium items with concrete.

Method of Application

Surface Preparation

Concrete

Surface must be sound, dry, clean and free from laitance, ice, standing water, grease, oils or coatings and all loose or friable particles must be removed to achieve a laitance and contaminant free, open textured surface.

The information contained in this technical data sheet is given to the best of our knowledge and the results from extensive testing in order to remain as objective as possible. However, it cannot, in any case be considered as a warranty involving our liability in case of misuse or any different use of our products from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users Consult the latest update of the technical data sheet on our website www.bluskyscpl.com

BLUSKY SPECILITY CHEMICALS PVT LTD | Registered & Corporate Office : T/F UNIT NO 330, VARDHAMAN, PLUS CITI MALL
LSC, SECTOR 23, DHULSIRAS, NEW DELHI – 110077, INDIA. Customer Care: Mob: +913 8076638589 , Email:
Customer.care@bluskyscpl.com

Steel

Must be cleaned and prepared thoroughly to an acceptance quality i.e. by blast cleaning and vacuum. Avoid dew point conditions.

Mixing

Mix parts A+B together for at least 3 minutes with a mixing spindle attached to a slow speed electric drill (max. 600 rpm) until the material becomes smooth in consistency and a uniform grey colour. Avoid aeration while mixing.

Application

When using a thin layer adhesive, apply the mixed adhesive to the prepared surface with a spatula, trowel, notched trowel, (or with hands protected by gloves). Ensure the surface temperature is in between +5°C to 40°C and 3°C above due point.

Advantages

- Easy to mix and apply as it is in paste consistency form.
- Suitable for dry and damp concrete surfaces.
- Very good adhesion to most construction materials.
- Fast setting and High early Strength.
- Hardens without shrinkage.
- No primer needed.
- Good abrasion and chemical resistance.
- Solvent free, high initial and ultimate strength
- Thixotropic: non-sag and suitable for vertical and overhead application



BLUSKY™ FLOWCRETE EPF

Solvent Free Thixotropic Epoxy Based Concrete Resurfacing Compound

Shelf Life & Storage

12 months from the date of manufacturing when stored in un-opened, original sealed and dry condition at a temperature range from +5°C to 40°C

Packing

4.5kg (Combined), Pack – A (Base) – 3kg, Pack – B (Hardener)
- 1.5kg

Precautions

- Store the material at the 5° to 40°C temperature range in shaded cool place and keep it away from fire and any heated body. Clean all tools with MEK or any standard solvent before polymerization starts.
- Application shall be carried out at below 70% RH and at least 3°C above the dew point.
- Mix only sufficient materials for immediate requirements.

Safety

- Wear hand gloves, safety shoes and safety goggles while using and handling the product.
- In case eyes or mouth are affected wash with plenty of clean water and seek medical treatment immediately.

Before use, refer to the Material Safety Data Sheet. The MSDS is available on www.bluskyscpl.com

The information contained in this technical data sheet is given to the best of our knowledge and the results from extensive testing in order to remain as objective as possible. However, it cannot, in any case be considered as a warranty involving our liability in case of misuse or any different use of our products from the “Application” paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users Consult the latest update of the technical data sheet on our website www.bluskyscpl.com